



# Epoxy.com Product #1W

## 100% Solids High-Build Epoxy Wall Coating

Thicker Bodied Epoxy Coating for use on Verticals and Overhead

### DESCRIPTION

**Product #1W High Build Epoxy Wall Coating** - epoxy coating for walls, is a two component, 100% solids epoxy Hi-Build epoxy wall coating used for high indoor traffic areas where abrasion resistance is required; for protection against mild corrosion; and as a decorative waterproof coating for walls, tanks, etc.

### ADVANTAGES

- *Moisture Insensitive*
- *Ceramic like finish*
- Thicker Bodied Epoxy Makes it an Excellent for Floors and Ceilings
- *Solvent Free*
- *Waterproof*
- *Extremely Durable*
- *Chemical Resistant*

### SURFACE PREPARATION

Surfaces to receive **Product #1W High Build Epoxy Wall Coating** must be clean and sound. Remove all dirt, laitance, grease curing compounds and other foreign matter by sandblasting, mechanical abrasion, or acid etching. Remove water and dust from all surfaces with an oil-free blast immediately prior to application.

### MIXING INSTRUCTIONS

Temperature of **Product #1W High Build Epoxy Wall Coating** must be 50 degrees F or above at time of mixing. Stir each component separately before blending. Mix 4 parts by volume of Part A with 1 part by volume of Part B for three minutes with a low speed electric drill motor equipped with a mixing paddle

### APPLICATION

Apply **Product #1W High Build Epoxy Wall Coating** with a roller, brush, or spray equipment. Two coats are recommended. Thickness per coat should be 7-10 mils. Seven days cure time is required to reach maximum chemical resistance.

### LIMITATIONS

**DO NOT** apply **Product #1W High Build Epoxy Wall Coating** at temperatures below 40° F. Surface must be dry.

## SAFETY PRECAUTIONS

**Prolonged or repeated exposure may cause eye and skin irritation. If contact occurs, wash immediately and seek medical help. Use safety glasses with side shields and wear protective rubber gloves.**

## CLEANING

Clean **Product #1W High Build Epoxy Wall Coating** from all tools and equipment should be cleaned before the system gels. Use MEK, Acetone, or any lacquer solvent.

## APPLICATION PROPERTIES @77° F

Mix Ratio	4:1 By Volume
Viscosity (mixed)	2000 -2500 CPS
Pot Life (200 gr.)	40-50 minutes
Tack Free to Touch	8 to 10 Hours
Initial Cure	24 Hours
Final Cure	7 Days
Packaging Unit Size	1.25 gal. unit, 5 gallon unit
Standard Colors	White, Light Gray, Dark Gray, Taupe, Sand, Old Gold, Mocha, Brick Red, Slate Blue, Colonial Green, Deep Blue, Black, Safety Yellow

## TENSILE PROPERTIES

Tensile Strength (ASTM D-638) 5500 psi. min.

Elongation 4-5%

**FOR INDUSTRIAL USE ONLY KEEP AWAY FROM CHILDREN**

For more information please contact:

[Epoxy.com](http://Epoxy.com).

**352-489-1666 (Phone)**

**352-465-3497 (Fax)**

[info@epoxy.com](mailto:info@epoxy.com)

[www.epoxy.com](http://www.epoxy.com)

Epoxy.com a division of Epoxy Systems, Inc. warrants this products (when properly stored) for one Epoxy.com warrants that its products will be free of manufacturing defects and will be in conformity with published specifications when handled, stored, mixed and applied in accordance with recommendations of Epoxy.com. If any product fails to meet this warranty, the liability of Epoxy.com will be limited to replacement of any non-conforming material if notice of such non-conformity is given to Epoxy.com within the warranty period for the material (as indicated above), or within 1 year of the delivery of materials (whichever is sooner). Epoxy.com may in its discretion refund the price received by Epoxy.com in lieu of replacing the material. No customer, distributor, or representative of Epoxy.com is authorized to change or modify the published specifications of this warranty in any way. No one is authorized to make oral warranties on behalf of Epoxy.com. In order to obtain replacement or refund the customer must provide written notice containing full details of the non-conformity. Epoxy.com reserves the right to inspect the non-conforming material prior to replacement. EXCEPT FOR THE EXPRESSED WARRANTY STATED ABOVE, THERE ARE NO OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR PURPOSE. Epoxy.com 'S OBLIGATION SHALL NOT EXTEND BEYOND THE OBLIGATIONS EXPRESSLY UNDERTAKEN ABOVE AND Epoxy.com SHALL HAVE NO LIABILITY OR RESPONSIBILITY TO THE PURCHASER OR ANY THIRD PARTY FOR ANY LOSS, COST, EXPENSE, DAMAGE OR LIABILITY, WHETHER DIRECT OR INDIRECT, OR FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES. All quotes and sales subject to availability.

