



Epoxy.com Product #28

Epoxy Mortar

DESCRIPTION

Epoxy.com PRODUCT #28 is a multipurpose colored epoxy binder for Epoxy.com Mortar Systems. This all purpose epoxy resin is characterized as an excellent general purpose material with good clarity and color retention. It is essentially odorless and can therefore be used in occupied areas.

ADVANTAGES

- Good troweling properties
- Excellent color retention
- Low odor for use in occupied areas.
- Low viscosity good wetting properties
- Available in "fast cure" systems.

CONSIDERATIONS

- Minimum application temperature of 50°F (Contact **Epoxy System, Inc.** for Low Temperature Cure).
- Substrate must be free of curing agents and any foreign materials.
- Slight color variation can be expected from batch to batch.
- Pigmented version should not be used as a coating.

COMPOSITION

100% solids amine cured Epoxy Resin.

APPLICATION

SURFACE PREPARATION

Surface Preparation is the most critical portion to any successful resinous flooring system application. All substrates must be properly prepared as outlined in **Epoxy.com** Surface Preparation Procedures. Work must be performed by trained or experienced contractors or maintenance personnel. The Epoxy.com technical service department is pleased to answer any questions.

INSTALLATION

Will vary with application method.

PHYSICAL PROPERTIES	
Color	Clear to Slightly Amber
Gloss, 60°F	85-1 00
Weight/gallon	9.00-9.5 mixed
Solids Content	100%
Mix Ratio	4A to I B by volume
Pot Life	30-40 minutes @ 70°F
Viscosity	950 cps, mixed approx.
VOC	0
10-20 mil film	10-14 hrs.
Light Traffic	16 hrs.
Ultimate Cure 74°F	5 days
@ 50°F	14 days

DRY TIME

CHEMICAL RESISTANCE

R-Recommended for continuous service. L-Limited recommendation, occasional spills.

REAGENT	RATING	REAGENT	RATING
Acetic Acid-5%	L	Lactic Acid-15%	R
Acetone	L	Methyl Ethyl Ketone	L
Bleach	L	Nitric Acid-10%	R
Citric Acid-30%	R	Skydrol	R
Crude Oil	R	Sodium Hydroxide-50%	R
Diesel Fuel	R	Sulfuric Acid-20%	R
Ethylene Glycol	R	Toluene	R
Fatty Acids	L	Urea	R
Gasoline	R	Vinegar	L
Hydrochloric Acid-15%	R	Xylene	R

PERFORMANCE PROPERTIES

Tensile Strength ASTM-D-638	8500 p.s.i
Elongation ASTM-D-638	5.5%
Adhesion to metal	2500 p.s.i
Adhesion to concrete ACI Committee 403	350 p.s.i (concrete fails)
Hardness ASTM-D-2240	80 (Shore D)
Abrasion Resistance ASTM-C-501	35-40 mg loss (CS-17 wheel, 1 kg load, 1000 cycles)
Service Temperature MIL- D-3134F	160 F (immersion) 185 F (dry heat)
Impact Resistance MIL-D3134F § 4.7.3	Withstands 16ft/lbs. no cracking, delamination or chipping.
Indentation MIL-D-3134F § 4.7.4	Withstands 2,000 lbs./sq. in. for 30 min. without indentation.
Elevated Temperature Resistance MIL-D-31 34F §4 7 5	No slip or flow at required temperatures at 158 degrees F
Water Absorption ASTM-D-670-63 (24. hr. immersion)	0.10% maximum
Flexural Strength ASTM-D-790	8,000 p.s.i
Compressive Strength ASTM-D-695	11,000 p.s.i

**FOR INDUSTRIAL USE ONLY
KEEP AWAY FROM CHILDREN**

For more information please contact:

Epoxy.com.

352-489-1666 (Phone)

352-465-3497 (Fax)

info@epoxy.com

www.epoxy.com

Epoxy.com a division of Epoxy Systems, Inc. warrants its products (when properly stored) for the period of time as follows: Epoxies, Product #315, Product #315BC, and Product #316 one (1) year; Polyesters, Methyl Methacrylates (normal) two (2) months and Polyurethanes Four (4) months; Power Tools and Equipment 90 days; Vinyl Esters, High Molecular Weight Methacrylates (HMMA) and all other resins (not specifically mentioned above) 30 days; hand tools (non-power tools) 30 days. Epoxy.com warrants that its products will be free of manufacturing defects and will be in conformity with published specifications when handled, stored, mixed and applied in accordance with recommendations of Epoxy.com. If any product fails to meet this warranty, the liability of Epoxy.com will be limited to replacement of any non-conforming material if notice of such non-conformity is given to Epoxy.com within the warranty period for the material (as indicated above), or within 1 year of the delivery of materials (whichever is sooner). Epoxy.com may in its discretion refund the price received by Epoxy.com in lieu of replacing the material. No customer, distributor, or representative of Epoxy.com is authorized to change or modify the published specifications of this warranty in any way. No one is authorized to make oral warranties on behalf of Epoxy.com. In order to obtain replacement or refund the customer must provide written notice containing full details of the non-conformity. Epoxy.com reserves the right to inspect the non-conforming material prior to replacement. EXCEPT FOR THE EXPRESSED WARRANTY STATED ABOVE, THERE ARE NO OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR PURPOSE. Epoxy.com'S OBLIGATION SHALL NOT EXTEND BEYOND THE OBLIGATIONS EXPRESSLY UNDERTAKEN ABOVE AND Epoxy.com SHALL HAVE NO LIABILITY OR RESPONSIBILITY TO THE PURCHASER OR ANY THIRD PARTY FOR ANY LOSS, COST, EXPENSE, DAMAGE OR LIABILITY, WHETHER DIRECT OR INDIRECT, OR FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES. All quotes and sales subject to availability.